

Application No. 09/588,407
GAU 1733
Filed June 6, 2000

AMENDMENT TO CLAIMS

With respect to the above-identified Office Action, the proposed following amendment is offered for consideration in order to place the Claims in better condition for appeal.

1. (Currently Amended) An inflatable heating device comprising:
a generally cylindrical body having an inner surface and an outer surface, said inner surface of said cylindrical body of the heating device defining a generally hollow inflation chamber, said body including a flexible matrix and a plurality of nonmetallic, electrically conductive fibers comprising carbon fibers, graphite fibers, carbon filaments or graphite filaments, said fibers embedded within said flexible matrix, said flexible matrix being cured to a stable elastomeric state by electrical resistive heating of said fibers, said body being capable of expanding and returning to an original form, and electrical cable lines connecting the electrically conductive fibers in the generally cylindrical body to an electrical energy source for providing electrical energy to the electrically conductive fibers to resistively heat the electrically conductive fibers.
2. (Previously Presented) The inflatable heating device of claim 1 wherein said flexible matrix comprises one or more materials selected from the group consisting of fluorosilicone and fluorocarbon.
3. (Cancelled)
4. (Previously Presented) The inflatable heating device of claim 1 wherein said fibers are arranged helically and positioned at an angle of +/- 45° with respect to the longitudinal axis of said body.
5. (Previously Presented) The inflatable heating device of claim 4 wherein said fibers are arranged in one of tows and bundles to provide approximately 50-90% coverage of said body.
6. (Previously Presented) The inflatable heating device of claim 1 wherein said fibers comprise a non-woven tape.
7. (Withdrawn) A process of forming an inflatable heating device comprising the steps of applying a layer of uncured sheets of a fluorosilicone material to a mandrel;

Application No. 09/588,407
GAU 1733
Filed June 8, 2000

winding a plurality of carbon fiber in a helix onto said fluorosilicone material layer;
applying a layer of uncured sheets of fluorocarbon material over said carbon fibers;

applying a radially inward pressure to said fluorosilicone layer, carbon fibers and fluorocarbon layer; and

applying an electric current to said carbon fibers to resistively heat said carbon fibers to cure said fluorosilicone layer and said fluorocarbon layer to form a cured structure.

8. (Withdrawn) The process of claim 7 further comprising the steps of removing said electric current from said carbon fibers;

removing said radially inward pressure from said fluorosilicone layer;

carbon fibers and fluorocarbon layer;

allowing said cured structure to cool; and

removing said cured structure from said mandrel.

9. (Withdrawn) The process of claim 7 wherein said applying an electric current step comprises resistively heating said carbon fibers to heat said fluorosilicone layer and said fluorocarbon layer to a temperature of approximately 300°F for approximately 45 minutes.

10. (Withdrawn) The process of claim 9 further comprising removing said fluorosilicone layer, carbon fibers and fluorocarbon layer from said mandrel, and heating said fluorosilicone layer, carbon fibers and fluorocarbon layer to a temperature greater than 300°F.

11. (Withdrawn) The process of claim 7 further comprising incorporating a layer of uncured silicon sheets in said cured structure.

12. (Currently Amended) An apparatus for curing a pre-preg repair material supporting a heat curable resin for in-situ repair of a conduit, comprising:

an elastomeric composite having a first end and a second end, wherein the composite includes a non-ferrous heating element comprised of carbon fibers, graphite fibers, carbon filaments or graphite filaments and disposed within a thermoset resin matrix;

Application No. 09/588,407
GAU 1733
Filed June 8, 2000

a first end piece fixedly attached to the first end of the composite and having an air port for communication with a compressed air source, a vacuum port for communication with a vacuum supply source and at least one electrical cable port to convey electric current to the non-ferrous heating element from a power supply source; and

a second end piece fixedly attached to the second end of the composite, wherein the composite, the first end piece, and the second end piece form a generally hollow inflation chamber.

13. (Original) The apparatus of Claim 12 wherein the thermoset resin is selected from the group consisting of fluorocarbon and fluorosilicone.

14. (Previously Presented) The apparatus of Claim 12 wherein the heating element includes a plurality of braided fibers comprising temperature tolerant fiber braids and electrically conductive fiber braids.

15. (Original) The apparatus of Claim 14 wherein the braided fibers interact to define a braid angle measure at +/- 45 degrees.

16. (Original) The apparatus of Claim 14 wherein the electrically conductive fiber braids are carbon filaments.

17. (Canceled)

18. (Currently Amended) ~~The apparatus of Claim 12 wherein the heating element includes a plurality of filament wound fibers comprising of temperature tolerant fiber windings and electrically conductive fiber windings.~~

An apparatus for curing a pre-preg repair material supporting a heat curable resin for in-situ repair of a conduit, comprising:

an elastomeric composite having a first end and a second end, wherein the composite includes a non-ferrous heating element comprised of a plurality of filament wound carbon fibers, filament wound graphite fibers, filament wound carbon filaments or filament wound graphite filaments and disposed within a thermoset resin matrix;

a first end piece fixedly attached to the first end of the composite and having an air port for communication with a compressed air source, a vacuum port for

Application No. 09/588,407
GAU 1733
Filed June 6, 2000

communication with a vacuum supply source and at least one electrical cable port to convey electric current to the non-ferrous heating element from a power supply source; and

a second end piece fixedly attached to the second end of the composite, wherein the composite, the first end piece, and the second end piece form a generally hollow inflation chamber.

19. (Previously Presented) The apparatus of Claim 18 wherein the wound fibers interact to define an angle measure at +/- 45 degrees.

20. (Currently Amended) A method for repairing a damaged section of a conduit comprising the steps of:

providing an elastomeric composite having a first and second end, wherein the composite includes a non-ferrous electrically conductive heating element comprising carbon fibers, graphite fibers, carbon filaments or graphite filaments and disposed within a thermoset resin matrix;

fixedly attaching a first and second end piece respectively to the first and second ends of the composite, wherein the first end piece, the second end piece, and the composite form a heating/inflation module;

removably attaching a pre-preg to an outer surface of the composite, wherein the pre-preg includes a structural fiber matrix supporting a heat curable resin;

positioning the module with the attached pre-preg into the conduit at a damaged location;

inflating the module to a predetermined internal air pressure to expand the composite and press the pre-preg against an inside surface of the conduit;

curing the resin of the pre-preg by causing an electrical current to flow in the heating element to resistively heat the module to a predetermined temperature; and

deflating the module and removing it from the conduit.

21. (Cancelled)

22. (Currently Amended) A system for in-situ repair of a conduit, comprising:

an apparatus including an elastomeric composite having a first end and a second end, wherein the composite includes a non-ferrous heating element

Application No. 09/588,407
GAU 1733
Filed June 6, 2000

comprising carbon fibers, graphite fibers, carbon filaments or graphite filaments and
disposed within a thermoset resin matrix;

a first end piece fixedly attached to the first end of the composite and
having an air port for communication with a compressed air source, a vacuum port
for communication with a vacuum supply source and at least one electrical cable
port to convey electric current to the non-ferrous heating element from a power
supply source;

a second end piece fixedly attached to the second end of the composite, wherein
the composite, the first end piece, and the second end piece form an inflation
chamber; and,

a pre-preg removably attached to an outer surface of the composite of the
apparatus, the pre-preg including a structural fiber matrix supporting a heat curable
resin.

23. (Withdrawn) A method for in-situ repair of a conduit comprising:

providing a generally cylindrical body having an inner surface and an outer
surface, said body containing a flexible elastomeric matrix and a plurality of
nonmetallic conductive fibers arranged helically about said body so as to expand
and contract and contract with the application of air pressure and vacuum pressure
to said inner surface of said body;

providing an electrical power source connected to said fibers;

resistively heating said fibers by the electrical power source to cure the
elastomeric matrix of the cylindrical body;

providing a pre-preg removably attached to an outer surface of said body; and

resistively heating said fibers by the electrical power source to cure the pre-preg.

24. (Withdrawn) The method of claim 23 further comprising providing a controller to
monitor and vary the temperature of the fibers.

25. (Withdrawn) The method of claim 24 further comprising monitoring and varying the
temperature of said fibers to achieve a uniform cure in the pre providing a pre-preg
removably attached to an outer surface of said body; and, resistively heating said fibers
by the electrical power source to cure the pre-preg.

Application No. 09/588,407
GAU 1733
Filed June 8, 2000

26. (Currently Amended) An inflatable heating device having a generally cylindrical body for internal in-situ repair of pipe shaped objects comprising:

an elastomeric seamless composite closed body having a generally cylindrical shape formed of at least one layer of a flexible elastomeric material having a first inner surface and a second outer surface, a plurality of nonmetallic, electrically conductive fibers comprising carbon fibers, graphite fibers, carbon filament or graphite filaments and located substantially throughout the length of the cylindrical shaped body between the first inner surface and second outer surface of the flexible elastomeric material;

at least one electrically conductive cable port connecting the electrically conductive fibers to an electrical power source; and

at least one air port for inflation and deflation of the closed body.

27. (Previously Presented) The inflatable heating device of Claim 26 wherein the generally cylindrical body has an outer diameter sized to allow the second outer surface to contact an inner surface of a repair object to transfer electrical resistive heat energy created by the conductive fibers located between the first inner surface layer and second outer surface layer when energized by the electrical power source and the body is inflated.

28. (Previously Presented) The inflatable heating device of Claim 26 further comprising components to monitor heat of the composite body and to control resistive heating.

Claims 29-52 (Canceled)